

## “PH-30” PLASTICIZING AGENT

(BITUMINOUS FLEX) COMPANY STANDARD 04386077-002-2017



### INTENDED USE

The agent is intended for the production of polymer-bituminous binder.



### TECHNICAL SPECIFICATIONS

- Density at 15 °C: 955 (940-970) kg/m<sup>3</sup>
- Kinematic viscosity at 100 °C: 325-650 mm<sup>2</sup>/s
- Dynamic viscosity at 60 °C: 3.0-4.3
- Flash point in open crucible: at least 230 °C
- Water content, %: no



### APPLICATION

To be introduced in conjunction with SBS polymer



### CONSUMPTION RATE

The percentage of addition to polymer-bituminous binder: 1 - 6%.



### STORAGE

Form of supply: 200 l metal barrels, truck loading  
No special storage conditions required.

## “PH-35” PLASTICIZING AGENT

COMPANY STANDARD 04386077-02-2016



### INTENDED USE

The agent is intended for the production of polymer-bituminous binder.



### TECHNICAL SPECIFICATIONS

- Density at 20 °C: 950 kg/m<sup>3</sup>
- Kinematic viscosity at 80 °C: 23
- Flash point in open crucible: 232 °C
- Water content: no
- Flow point: 18 °C



### APPLICATION

To be introduced in conjunction with SBS polymer.



### CONSUMPTION RATE

The percentage of addition to polymer-bituminous binder: 1-6%.



### STORAGE

Form of supply: 200 l metal barrels, truck loading  
No special storage conditions required.